

# **Technical Data Sheet**



BIOflex FL is a 15 oz. front-lit, biodegradable banner/billboard material. BIOflex is coated and very similar in all around performance to Ultima Supreme. In landfill conditions (darkness, high heat, moisture and lack of oxygen), BIOflex attracts microbes that break down the PVC within 3 to 5 years. It is latex compatible and contains no toxic materials, making it a functional, environmentally progressive PVC substrate. Widths range from 54" -196".



#### **Material Details**

CHARACTERISTICS	TEST METHOD	METRIC	ENGLISH	
Support Cloth	DIN ISO 2076	Polyester	Polyester	
Yarn dtex	DIN EN ISO 2060	1100 x 1100 dtex	1000 x 1000 denier	
Type of Coating	N/A	PVC	PVC	
Total Weight	DIN EN ISO 2286-2	510 g/m <sup>2</sup>	15 oz/yd²	
Tensile Strength	DIN EN ISO 1421	2400 x 2200 N/5cm	274 x 251 lbs/inch	
Tear Strength (warp/weft)	DIN 53363	250 x 250 N	56 x 56 lbs	
Flame Resistance	DIN 75200	NFPA701, Title 19, CSFM, B1		
Low Temperature (No Crack at:)	ISO 1876	Low at -18°C	Low at -0°F	
RF Weldable (Heat Sealable)	DIN 53354	Yes	Yes	
Fungus Resistant	ASTM G21	Treated		

## **Applications**

	Backlit	Banner	Billboard	Blockout	Building Wrap	Display Systems	Truckside
Applications							

## **Ink Printability**

Solvent	Eco Solvent	UV	Latex	Screen Printing	Dye Transfer	Dye Direct

### **Available Sizes**

Metric (m)	English (inches)		
1.37, 1.60, 1.83,	54, 63, 72, 98, 126,		
2.50, 3.20, 5.00	196		

Key: ■ - Excellent □ - Good

The information on physical and chemical characteristics is based upon tests believed to be reliable. The values are intended only as a source of information. A legally binding guarantee of specific properties is not to be inferred from our specifications. They are given without guaranty and do not constitute a warranty. The purchaser should independently determine, prior to use, the suitability of this material for his/her specific purpose. (Data represents averages and is not intended for use as a specification.)